

NAS254NM (UNS N08367)

High Corrosion Resistant Super Stainless Steel

NAS254NM (UNS N08367 equivalent) is a high corrosion resistant stainless steel with high contents of chromium and molybdenum, and provides excellent corrosion resistance under severe environments such as seawater and flue gas desulfurization plants. Depending on the environment, it can be an economical alternative to Nickel alloy and pure titanium. Nippon Yakin supplies this product in plate, sheet and strip form.

Steel Grade/Standard

Nippon Yakin Grade	JIS	ASTM A240/B688	EN
NAS254NM	—	UNS N08367	—

Chemical Composition

	C	Si	Mn	P	S	Ni	Cr	Mo	Cu	N	[wt %]
Specification* (UNS N08367)	≤0.030	≤1.00	≤2.00	≤0.040	≤0.030	23.5~ 25.5	20.0~ 22.0	6.0~ 7.0	≤0.75	0.18~ 0.25	

*ASTM A240

Physical Properties

Density	[g/cm ³]	8.06
Specific heat	[J/kg · K]	451
Electrical resistivity	[μΩ · cm]	94.4
Thermal conductivity	[W/m · K]	20°C 11.9
Average coefficient of thermal expansion	[10 ⁻⁶ /°C]	20~100°C 14.8
		20~200°C 15.3
		20~300°C 15.6
		20~400°C 15.9
Young's modulus	[MPa]	19.8 × 10 ⁴
Magnetism		None
Melting range	[°C]	1360~1394



NIPPON YAKIN KOGYO CO., LTD.

Mechanical Properties

Mechanical Properties at Room Temperature

		0.2% proof stress [MPa]	Tensile strength [MPa]	Elongation [%]	Hardness [HRBW]
Specification* (UNS N08367)	Sheet and strip	≥310	≥690	≥30	≤100
	Plate	≥310	≥655	≥30	≤241 (HBW)
Example	Hot-rolled plate 6.0mm [†]	422	770	49	207 (HBW)

*ASTM A240

Corrosion Resistance

Because NAS254NM contains high concentrations of chromium and molybdenum and also contains nitrogen, it offers excellent pitting corrosion resistance and crevice corrosion resistance in chloride environments. NAS254NM demonstrates excellent corrosion resistance under corrosion environments where it had been difficult to maintain corrosion resistance with conventional duplex stainless steels.

Pitting Corrosion Resistance

Alloy	ASTM G48 Method A		ASTM G48 Method C
	22°C	50°C	Critical pitting corrosion temperature CPT (°C)
NAS255	○	×	50
NAS329J3L	○	×	50
NAS64	○	○	55
NAS254NM	○	○	70

Test conditions ASTM G48 Method A (○: No pitting corrosion, ×: Pitting corrosion)

- Test solution: 6%FeCl₃
- Test temperature: 22°C, 50°C (Recommended temperature in this test)
- Test time: 72h

ASTM G48 Method C

- Test solution: 6%FeCl₃ + 1%HCl
- Test time: 72h

Crevice Corrosion Resistance

Alloy	ASTM G48 Method D	
	Critical crevice corrosion temperature CCT (°C)	
NAS255	10	
NAS329J3L	25	
NAS64	30	
NAS254NM	45	

Test conditions ASTM G48 Method D

- Test solution: 6%FeCl₃ + 1%HCl
- Test time: 72h

Acid Resistance

Alloy	Corrosion rate in sulfuric acid at 80°C (mm/y)					
	5%	10%	20%	40%	60%	80%
NAS255	<0.01	<0.01	0.78	2.95	0.48	5.01
NAS329J3L	0.01	0.17	4.65	365.9	1456	106.4
NAS64	<0.01	0.02	1.07	191.9	1054	60.72
NAS254NM	<0.01	0.03	0.79	2.58	1.82	7.66

Test time: 24h

Alloy	Corrosion rate in hydrochloric acid at 80°C (mm/y)			
	0.1%	1%	2%	3%
NAS255	<0.01	0.01	2.70	3.72
NAS329J3L	0.02	0.03	31.10	60.62
NAS64	0.01	0.01	12.94	30.51
NAS254NM	0.01	0.02	0.01	8.08

Test time: 24h

(Reference)

Alloy	JIS	UNS No.	Chemical composition
NAS255	SUS890L	N08904	20Cr-24Ni-4.3Mo-1.5Cu
NAS329J3L	SUS329J3L	S32205	22Cr-5.3Ni-3.2Mo-0.16N
NAS64	SUS329J4L	S32506	25Cr-6.5Ni-3.3Mo-0.17N
NAS254NM	—	N08367	21Cr-24Ni-6Mo-0.2N

Workability

Cold and hot workability are approximately equal to those of Type 304, 316, and other standard austenitic stainless steels. However, care is necessary for both cold and hot worked materials because they have high strength.

Weldability

Possible welding methods include shielded metal arc welding, TIG welding, and plasma welding, in the same manner as with standard austenitic stainless steels. As welding consumables, Alloy 276 should be used. Preheating and post-welding heat treatment are not necessary.

Machinability

As a distinctive feature of high Ni stainless steels, machinability is difficult in comparison with the austenitic stainless steels, but is easier than with Ni-based alloys. Use of a superhard tool whenever possible, together with a slow feed speed and large cut depth, is advised.

Heat Treatment

Solution annealing of NAS254NM should be performed at 1105°C and higher followed by being quenched in water or rapidly cooled by other means. (Conditions provided in ASTM A480/A480M)

Pickling

A mixture of nitric acid and hydrofluoric acid is used in pickling. However, due to the high corrosion resistance of NAS254NM, scale is somewhat difficult to remove in comparison with Type 304. Therefore, the material should be immersed in an alkaline solution before pickling, or if possible, shot blasting is extremely effective.

Applications

Chemical plants, Flue gas desulfurization plants, Heat exchangers.

For more information, please contact:

Nippon Yakin Kogyo Co., Ltd.
Material Solutions Sales Department
San-Ei Bldg., 5-8, 1-chome Kyobashi, Chuo-ku,
Tokyo 104-8365 Japan
TEL: +81-3-3273-4649 FAX: +81-3-3273-4642
URL: <https://www.nyk.co.jp/en/>

Note regarding the handling of property data:

The technical information contained in this product guide is representative values obtained in property tests and other items used to explain the performance of the product. With the exception of items specifically mentioned as provisions of a "Standard," the contents do not represent guaranteed upper limit or lower limit values. The respective data given on this technical information are typical examples and may be different in some cases from the data obtained from the actual product. No responsibility shall, therefore, be assumed for damages arising from using the technical information data. This information is also subject to change in the future without notice. To obtain the most recent information, please contact Nippon Yakin.
No part of this document may be copied or reproduced in any form without the consent of Nippon Yakin.